



Application technology

Dip-spinning

Spray

SPECIFIC PROCESSES

SPECIAL COATINGS FOR CHAINS

Description

GALOL, has developed a specific coating system by requirement of its customers (steel chain manufacturers and users of these items). The aim is to minimize wear and rupture of pins and links.

- Issues caused by friction, which induces excessive tension producing lengthening (loosening) or fatigue rupture of the links.
- Environment corrosion produces oxide and increases across time. Oxide produces mass loss and makes the links to weaken.
- Presence of hydrogen in the steel structure generated during electroplating process can lead to brittle fracture of pins and links.
- The fracture of a link provokes the immediate stop of the assembly line and other indirect consequences, thus producing increase in costs to the companies..



General properties

- Galol, S.A., has developed the application of the product CAD-5 that helps solving the issues described above.
- It provides excellent lubrication properties and anti-galling properties because of its gliding agents.
- It also provides high corrosion protection that can reach 800 h in salt spray tests, making the use of stainless steel not necessary.
- Coating system free of risk of hydrogen embrittlement, since it does not introduce hydrogen into the steel part.
- Colour identification, with colours like silver, black and others.
- Non-toxic coating system. It can be used for machinery that manufacture products used in the food industry.

Uses

It can be applied to all types of chains, transmission chains, roller chains, assembled (depending on the size and length), unassembled, gears, rollers, etc.

THIS TREATMENT IS APPLIED DIRECTLY IN LINE OR IN COMBINATION WITH PREVIOUS AND SUBSEQUENT APPLICATIONS.

GALOL S.A. offers the possibility to reduce logistic costs between the different operations of manufacturing of the part.

GALOL S.A.

Camino de Montaverner, s/nº
E 46850 L'Olleria (Valencia)
Tel. 962 208 005
Http: www.galol.com
E-mail: galol@galol.com

